






BRICK® 600

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	600 microns	Non adhesive Polyester	    

APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	60°	80 gf	10 cm/sec	25 seconds	155°C (311°F)	medium/high (4 bar)	cold

NOTE: Due to the thickness of the material, we do not recommend cutting details of dimensions less than 0,5 cm

- Mirror cut the design
- Weed excess material
- Preheat the garment for 20 seconds
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier cold

- PRODUCT HIGHLIGHTS**
- Matt finish
 - Thickness adds dimension to any logo
 - Soft to the touch

NOTE: We highly recommend to perform a test, before launching a production!

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015
www.tuv.com
ID 9105027988

